## FUGRO TECHNICAL SERVICES LIMITED

Fugro Development Centre, 5 Lok Yi Street, Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel +852 2450 8233 : +852 2450 6138 Fax E-mail: matlab@fugro.com Website: www.fugro.com



Report No.

181004EN180628(3)



Page 1 of 1

## Test Report on Analysis of Paint

## Information Supplied by Client

Client

Hong Kong Niceview International Ltd.

Client's address

Flat H, 21/F., Golden Dragon Ind. Ctr., Block III, 172-180 Tai Lin

Pak Road, Kwai Chung, N.T.

**Project** 

HKGBC Green Building Product Labelling Scheme

Sample description

**Niceview Exterior Paint** 

Sample identification

Test required

Adhesion

**Laboratory Information** 

Lab sample ID

EN180628/1

Date of receipt of sample:

10/03/2018

Date test completed

26/03/2018

Test method used

ASTM D3359: 1997 Method B

## Results:

Testing item	Result
Adhesion test	Classification 4B
	(Small flakes of the coating are detached at intersections, less than 5% of the area is affected.)

Note: Thinning ratio – 10 parts of paint to 1 part of water by weight.

Supervised by : K.F. Wong

Certified by

pproved Signatory : HO Kin Man, John Manager - Chemistry Department

875/2018

Date \*\* End of Report \*\*

Note: This report refers only to the sample(s) tested.